

TECHNICAL CHARACTERISTICS OF RUBBER COATED FABRICS

| | Unit | Norm | Value | Tolerance |
|-----------------------------------|---------------|----------------------|-------------------|-----------------|
| Weight | g/sqmt | UNI EN ISO 2286-2 | 360 | +/- 25 |
| Gauge | mm | UNI EN ISO 2286-3 | 0,30 | +/- 0,02 |
| Tensile strength warp/weft | N/5cm | UNI EN ISO 1421 | ≥500/ ≥300 | |
| Air permability | KPa | Int. Novurania 10222 | ≥ 70 | |
| Working temperature | °C | | -20 +120 | |
| State of delivery | | | | cured |

CHARACTERISTICS OF TEXTILE REINFORCEMENT

| | Unit | Value |
|---------------------|---------------|---------------|
| Type of yarn | | CO/PES |
| Weight | g/sqmt | 70 |

CHARACTERISTICS OF COATING ELASTOMER

| | |
|--------------------------|--------------|
| Type of elastomer | NBR |
| Colour | black |