TT 2015 C

TECHNICAL CHARACTERISTICS OF RUBBER COATED FABRIC

	Unit	Norm	Value	Tolerance
Weight	**g/sqmt**	**UNI EN ISO 2286-2**	**480**	**+/- 48**
Gauge	**mm**	**UNI EN ISO 2286-3**	**0.85**	**+/- 0.09**
Tensile strength warp & weft	**N/5cm**	**UNI EN ISO 1421**	**≥1800/ ≥1200**	
Coating adhesion	**N/5cm**	**Int. Novurania I0396**	**≥ 100**	
Working temperature	**°C**		**-30 +90**	
State of delivery			**cured**	

CHARACTERISTICS OF TEXTILE REIFORCEMENT

	Unit	Value	
Type of yarn		**PES / PES**	**(2 plies)**
Weight	**g/sqmt**	**160 / 60**	
Construction	**dTex**	**taffeta / twill**	
Colour		**black / black**	

CHARACTERISTICS OF COATING ELASTOMER

Type of polymer IIR

APPLICATIONS

Dry-suits

PROVISIONAL DATA SHEET

Novurania declines any responsibility for any damage or problem coming from a wrong usage of the product.

Issuing date 22th of June 2015 Revision: 0