

TECHNICAL CHARACTERISTICS OF RUBBER COATED FABRICS

| | Unit | Norm | Value | Tolerance |
|-----------------------------------|---------------|----------------------|-----------------|-----------------|
| Weight | g/sqmt | UNI EN ISO 2286-2 | 2500 | +/- 200 |
| Gauge | mm | UNI EN ISO 2286-3 | 2,00 | +/- 0,20 |
| Tensile strength warp/weft | N/5cm | UNI EN ISO 1421 | ≥ 2500 | |
| Coating/fabric adhesion | N/5cm | Int. Novurania 10396 | ≥ 125 | |
| Working temperature | °C | | -20 +120 | |
| State of delivery | | | | cured |

CHARACTERISTICS OF TEXTILE REINFORCEMENT

| | Unit | Value |
|----------------------|---------------|------------|
| Type of yarn | | PA |
| Weight | g/sqmt | 230 |
| Title of yarn | dtex | 940 |

CHARACTERISTICS OF COATING ELASTOMER

| | |
|--------------------------|--------------|
| Type of elastomer | ECO |
| Colour | black |