

## TECHNICAL CHARACTERISTICS OF RUBBER COATED FABRICS

	Unit	Norm	Value	Tolerance
<b>Weight</b>	<b>g/sqmt</b>	UNI EN ISO 2286-2	<b>1300</b>	<b>+/-150</b>
<b>Gauge</b>	<b>mm</b>	UNI EN ISO 2286-3	<b>1,1</b>	<b>+/-0,15</b>
<b>Tensile strength warp/weft</b>	<b>N/5cm</b>	UNI EN ISO 1421	<b>≥1300/ ≥1100</b>	
<b>Coating adhesion</b>	<b>N/5cm</b>	Int. Novurania 10396	<b>≥ 125</b>	
<b>Working temperature</b>	<b>°C</b>		<b>-20 +120</b>	
<b>State of delivery</b>			<b>cured</b>	

## CHARACTERISTICS OF TEXTILE REINFORCEMENT

	Unit	Value
<b>Type of yarn</b>		<b>PA</b>
<b>Weight</b>	<b>g/sqmt</b>	<b>105</b>
<b>Construction</b>	<b>dtex</b>	<b>235 19 X 19</b>

## CHARACTERISTICS OF COATING ELASTOMER

<b>Type of elastomer</b>	<b>NBR</b>
<b>Colour</b>	<b>grey</b>
<b>Compound respecting norm (not resistant to ozone)</b>	<b>UNI EN 549 (class B2/H3)</b>