

## TECHNICAL CHARACTERISTICS OF RUBBER COATED FABRICS

	Unit	Norm	Value	Tolerance
<b>Weight</b>	<b>g/sqmt</b>	DIN EN ISO 2286-2	<b>1300</b>	<b>+/- 150</b>
<b>Gauge</b>	<b>mm</b>	DIN EN ISO 2286-2	<b>1,10</b>	<b>+/- 0,11</b>
<b>Tensile strength warp/weft</b>	<b>N/5cm</b>	UNI ISO 1421	<b>≥2000</b>	
<b>Coating adhesion</b>	<b>N/5cm</b>	Int. Novurania 10396	<b>≥ 100</b>	
<b>Working temperature</b>	<b>°C</b>		<b>-20 +100</b>	
<b>State of delivery</b>			<b>cured</b>	

## CHARACTERISTICS OF TEXTILE REINFORCEMENT

	Unit	Value
<b>Type of yarn</b>		<b>PA</b>
<b>Weight</b>	<b>g/sqmt</b>	<b>156</b>
<b>Construction</b>	<b>dtex</b>	<b>470 16 x 16</b>

## CHARACTERISTICS OF COATING ELASTOMER

<b>Type of elastomer</b>	<b>ECO</b>
<b>Colour</b>	<b>black</b>
<b>Compound approved for regulation</b>	<b>R110</b>