

# TT 055 A

## TECHNICAL CHARACTERISTICS OF RUBBER COATED FABRIC

	Unit	Norm	Value	Tolerance
<b>Weight</b>	<b>g/sqmt</b>	UNI EN ISO 2286-2	<b>2450</b>	<b>+/- 250</b>
<b>Gauge</b>	<b>mm</b>	UNI EN ISO 2286-3	<b>1.95</b>	<b>+/- 0,20</b>
<b>Tensile strength warp &amp; weft</b>	<b>N/5cm</b>	UNI EN ISO 1421	<b>≥2500/ ≥2500</b>	
<b>Coating fabric/adhesion</b>	<b>N/5cm</b>	Int. Novurania 10396	<b>≥35</b>	
<b>Working temperature</b>	<b>°C</b>		<b>-30 +120</b>	
<b>State of delivery</b>			<b>cured</b>	

## CHARACTERISTICS OF TEXTILE REINFORCEMENT

	Unit	Value
<b>Type of yarn</b>		<b>PA</b>
<b>Weight</b>	<b>g/m<sup>2</sup></b>	<b>260</b>
<b>Construction</b>	<b>dtex</b>	<b>940 11 x 12</b>

## CHARACTERISTICS OF COATING ELASTOMER

<b>Type of polymer</b>	<b>ECO</b>
<b>Colour</b>	<b>nero</b>

## APPLICATIONS

**Membranes**

### PROVISIONAL DATA SHEET

*Novurania declines any responsibility for any damage or problem coming from a wrong usage of the product.*

Issuing date 27<sup>th</sup> of December 2013

Revision: 0