

# TT 502 A

5165007

## TECHNICAL CHARACTERISTICS OF RUBBER COATED FABRICS

	Unit	Norm	Value	Tolerance
<b>Weight</b>	<b>g/sqmt</b>	UNI EN ISO 2286-2	<b>300</b>	<b>+/- 30</b>
<b>Gauge</b>	<b>mm</b>	UNI EN ISO 2286-3	<b>0,20</b>	<b>+/- 0,02</b>
<b>Tensile strength HD/TD</b>	<b>N/5cm</b>	UNI EN ISO 1421	<b>≥200/ ≥150</b>	
<b>Air permeability</b>	<b>KPa</b>	Int. Novurania 10222	<b>≥ 70</b>	
<b>Working temperature</b>	<b>°C</b>		<b>-20 +120</b>	
<b>State of delivery</b>			<b>cured - semi cured -uncured</b>	

## CHARACTERISTICS OF REINFORCEMENT

	Unit	Value
<b>Film</b>		<b>PET</b>
<b>Weight</b>	<b>g/sqmt</b>	<b>35</b>

## CHARACTERISTICS OF COATING ELASTOMER

<b>Type of elastomer</b>	<b>NBR</b>
<b>Colour</b>	<b>azure</b>